

EPE FOAM / BACKER ROD

- ◆ EPE Foam / Backer Rod generally uses for gap filling as well used for expansion joint filling in floors.



PROPERTIES :-

PROPERTY	UNIT	Test Method	VALUE Observed
DENSITY	Kg/M ³	ASTMD3575	25.40
Elongation at Break	%	ASTMD3575	72.00
Tensile Strength	Kgf /Cm2	ASTMD3575	3.10
Water absorption at 27 Deg Centigrade for 48 Hrs	Change in Vol	ASTMD3575	0.03
Compression Set at 27 Deg Centigrade for 24 Hrs	%	ASTMD3575	8.50
Chemical Resistance			Excellent
Diameter	mm	ASTMD3575	6.70
Working Temperature	Degree Centigrade		(-)30 to (+)70

